

**Technical Data Sheet RoHS Compliant Product**  
**SFA07 Characteristics, MnZn**

**Material Characteristics:**

Material Properties	Symbol	Unit	Measuring Conditions			SFA07
			Freq.	Flux den.	Temp.	
Initial Permeability	$\mu_i$	-	$\leq 10\text{kHz}$	0.25mT	25°C	7000 $\pm$ 25%
Power Loss	$P_v$	kW/m <sup>3</sup>	25kHz	200mT	25 °C	-
					100°C	-
			100kHz	200mT	25 °C	-
					100°C	-
			300kHz	100mT	25 °C	-
					100°C	-
500kHz	50mT	25 °C	-			
		100°C	-			
Saturation Flux Density	$B_{ms}$	mT	10KHz	H=1200A/m	25°C	400
					100°C	200
Remanence	$B_{rms}$	mT	10KHz	H=1200A/m	25°C	150
					100°C	110
Coercivity	$H_c$	A/m	10kHz	H=1200A/m	25°C	-
					100°C	-
Relative Loss Factor	$\tan\delta / \mu_i$	$10^{-6}$	10KHz	$<0.25\text{mT}$	25°C	$<8$
			100kHz		25°C	$<30$
Hysteresis Material Constant	$\eta_B$	$10^{-6}/\text{mT}$	10KHz	1.5-3.0mT	25°C	$<1.2$
Disaccommodation Factor	$D_F$	$10^{-6}$	10KHz	$<0.25\text{mT}$	25°C	$<2$
Curie Temperature	$T_c$	°C	-	-	-	$\geq 130$
Resistivity	$\rho$	$\Omega\text{m}$	-	-	-	0.35
Density	$d$	g/cm <sup>3</sup>	-	-	-	4.9

Note: Material characteristics are typical for a toroid core.  
 Product specification will differ from these data due to the influence of geometry and size.

